

Product Description

DuPont™ Kalrez® 6221 perfluoroelastomer parts are compliant with the United States' Food and Drug Administration's regulations for repeated use in contact with food as described by 21 CFR177.2600 and Food Contact Notification 000101. Kalrez® parts made from compound 6221 have been tested in accordance with the United States Pharmacopoeia Class VI (USP Class VI) testing protocol and meet the test requirements of a USP Class VI polymer. This is a white product that offers excellent steam cycling resistance and reduces extractables from sealing materials to trace levels.

Typical Physical Properties¹

Color	White
Maximum Application Temperature ² , °C (°F)	260 (500)
Maximum Application Pressure ² , MPa (psi)	8.27 (1200)
Durometer, Shore A ³	70
Durometer, Shore M (o-ring)	
100% Modulus ⁴ , MPa (psi)	7.24 (1050)
Elongation at break ⁴ , %	150
Tensile at break ⁴ , MPa (psi)	15.16 (2200)
Compression set ⁵ , % (70 hours at 204°C (400°F))	
Pellet	27
Size 214 O-Ring	31
Specific Gravity, g/cc	2.18

¹Not to be used for specification

²DuPont proprietary test method – maximum application temperature and pressure may vary with seal design and application specifics

³ASTM D2240 (pellet test specimen)

⁴ASTM D412, 500mm/min

⁵ASTM D395B



Additional Physical Properties¹

Tg ² , °C (°F)	
TR-10 ³ , °C (°F)	-4 (24)
Brittle Point ⁴ , °C (°F)	
Linear Coefficient of Thermal Expansion, /°C (/°F)	3.07x10 ⁻⁴ (1.70x10 ⁻⁴)
Abrasion Resistance ⁵ , (volume loss, cubic mm)	105.6
Coefficient of friction ⁶ (to steel)	
Static	0.698
Dynamic	0.452
Volume resistivity ⁷ , ohms/square	
Surface resistivity ⁷ , Ohm-cm	
Dielectric Constant ⁸ at 150°C and 1 MHz	
Dissipation Factor ⁸ at 150°C and 1MHz	

¹Not to be used for specification

²DuPont proprietary test method – maximum application temperature and pressure may vary with seal design and application specifics

³ASTM D1329

⁴ASTM D746

⁵Din 53 516

⁶ASTM 1894

⁷ASTM D 257

⁸ASTM D150

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, and Vespel® are trademarks or registered trademarks of E. I. du Pont de Nemours and Company or its affiliates. All rights reserved.

Kalrez® Application Guide – September 2010



The miracles of science™