

Garlock STRESS SAVER® 3505



MATERIAL PROPERTIES*:

Color:	Blue
Composition:	PTFE with Aluminosilicate microspheres
Fluid Services (see chemical resistance guide):	Moderate concentrations of water treatment chemicals, potable water
Temperature¹, °F (°C)	
Minimum:	-450 (-268)
Maximum:	+500 (+260)
Ideal Operating Limit:	+400 (+204)
Pressure¹, Maximum, psig (bar):	
Minimum:	Full Vacuum
Maximum:	800 (55) in metal flanges
Ideal Operating Limit:	750 (52) in metal flanges
P x T (max.)¹, psig x °F (bar x °C):	250,000 (8,600)
Flammability:	Will Not Support Flame
Bacterial Growth:	Will Not Support
Meets Specifications:	FDA (Food and Drug Administration) 21 CFR 177.1550, USP (US Pharmacopeia), certified to NSF 61 (National Sanitation Foundation) for potable water

TYPICAL PHYSICAL PROPERTIES*:

ASTM F36	Compressibility, average, %:	12
ASTM F36	Recovery, %:	50
ASTM D1708	Tensile, Across Grain, psi (N/mm²):	2000 (13.8)
ASTM D792	Specific Gravity:	1.90
ASTM F586	Design Factors	
	"m" factor:	2.0
	"y" factor, psi (N/mm ²):	400 (2.7)

SEALING CHARACTERISTICS*

	DIN 3535 – Nitrogen
Gasket Load , psi (N/mm ²):	4640 (32)
Internal Pressure , psig (bar):	580 (40)
Leakage	<0.015 cc/min

Notes:

* This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties

¹ Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering. Minimum temperature rating is conservative.

8/15/2023