# Kalrez® Spectrum™ 7390



#### PERFLUOROELASTOMER PARTS

Kalrez® Spectrum™ 7390 perfluoroelastomer parts is a versatile FFKM product based on a patented proprietary crosslinking system that can meet your 90 durometer (Shore A) FFKM specifications in numerous shapes and configurations where higher mechanical strength is needed. Kalrez® Spectrum™ 7390 parts are designed to reliably seal in the most demanding chemical and hot water/steam environments. Thermally stable up to 300 °C, it is an ideal fit for upstream and downstream applications such as: oilfield production/completion equipment, wireline and drilling tools, steam-assisted gravity drainage (SAGD), cyclic steam stimulation (CSS), mechanical seals, valves, compressors, and process instrumentation.

#### **Product Information**

Colour Black

Maximum Service Temperature \* 300°C (572°F)

### Typical mechanical properties

Shore A hardness	89	ASTM D 2240
Modulus at 100% elongation	21.3 MPa (3090 psi)	ASTM D 412
Tensile Strength	22.1 MPa (3210 psi)	ASTM D 412
Elongation at Break	101 %	ASTM D 412
Compression Set, 70 hours at 204°C (400°F), O-ring (AS568-214)	14 %	ASTM D 1414

## Thermal Properties

Linear Coefficient of Thermal Expansion 2.34E-04 /°C (1.30E-04 /°F) ISO 11359-1/-2

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2021 DuPont. All rights reserved.

<sup>\*</sup>Maximum and Lowest Service temperatures may vary with seal design and application specifics.